



TECHNICAL DATA

Supply Point: **Douglasville, Georgia**

BUR Type III

CHARACTERISTICS	METHODS	UNITS	SPECIFICATIONS	
			ASTM D312	
			Min	Max
Specific Gravity @ 25°C (77°F)	ASTM D70	g/mL	Report	
Softening Point	ASTM D36	°C (°F)	85 (185)	96 (205)
Flash Point, (C.O.C)	ASTM D92	°C (°F)	302 (575)	-
Penetration @ 0°C (32°F) 200g, 60s	ASTM D5	dmm	6	-
Penetration @ 25°C (77°F) 100g, 5s	ASTM D5	dmm	15	35
Penetration @ 46°C(115°F) 50g, 5s	ASTM D5	dmm	-	90
Ductility @ 25°C (77°F) 5cm/min	ASTM D113	cm	2.5	-
Volatilization 5h, 163°C (325°F) Loss in weight	ASTM D6	%	Report	
Residue: penetration @ 25°C (77°F) 100g, 5 s	ASTM D5	% of original	80	-
Solubility in trichloroethylene	ASTM D2042	%	99.0	-
EVT 125 cP (mopping)	ASTM D4402	°C (°F)	-	221 (430)
EVT cP (mechanical)	75 ASTM D4402	°C (°F)	-	243 (470)

Meets ASTM D312 - 2015

Date of revision : August 15, 2016
by : M. Florant