



TECHNICAL DATA

Supply Point: **Montreal, Quebec**

BUR Type III

CHARACTERISTICS	METHODS	UNITS	SPECIFICATIONS	
			CSA A123.4-04	
			Min	Max
Specific Gravity 25°C (77°F) @	ASTM D70	g/mL	Report	
Softening Point	ASTM D36	°C (°F)	90 (194)	98 (208)
Flash Point, (C.O.C)	ASTM D92	°C (°F)	260 (500)	-
Penetration @ 0°C (32°F) 200g, 60s	ASTM D5	dmm	8	-
Penetration @ 25°C (77°F) 100g, 5s	ASTM D5	dmm	15	25
Penetration @ 45°C (113°F) 50g, 5s	ASTM D5	dmm	-	55
Ductility @ 25°C (77°F) 5cm/min	ASTM D113	cm	3.0	-
Volatilization 5h, 163°C (325°F) Loss in weight	ASTM D6	%	-	1.0
Residue: penetration @ 25°C (77°F) 100g, 5 s	ASTM D5	% of original	80	-
Solubility in trichloroethylene	ASTM D2042	%	99.0	-
EVT 125 cP (mopping)	ASTM D4402	°C (°F)	Report	
EVT cP (mechanical) 75	ASTM D4402	°C (°F)	Report	

Meets CSA A123.4 - 2004

Date of revision : August 15, 2016
by : M. Florant